#### **BONROY INTERNATIONAL LIMITED.**



ZIBO NEW MATERIAL TRADING CENTER, PLAZA A, NORTHEASTREN CORNER OF BEIJING ROAD AND RENMIN ROAD, ZHANGDIAN, ZIBO, SHANDONG, P.R. CHINA.

TEL: 0086-533-8170985

www.bonroy-int.com —

### **TECHNICAL DATA SHEET**

### PIP-BINDER® O-1098

**BONROY® O-1098** is 100% C5 Aliphatic hydrocarbon resin. It's general type C5 resin for hot melt adhesive which has good balance between initial adhesive and holding power.

The major usages of O-1098 are tackify a variety of adhesive polymers including natural rubber, synthetic polyisoprene, APAO, SIS and EVA.O-1098 also can be used in road marking paint and tire rubber.

## **SPECIFICATIONS**

Softening Point (Ring & Ball, ℃)	98 – 102	ASTM E 28
Initial Color (Yellow Index )	30 Max	ASTM D 6166
Wax Cloud Point (EVA/Resin/Wax=20/40/40)	100 Max	BDTM/Q-10

#### TYPICAL PROPERTIES

Softening Point (Ring & Ball, °C)	100	ASTM E 28
Initial Color (Yellow Index )	27	ASTM D 6166
(Ga)	3.5	ASTM D 616
Wax Cloud Point (EVA/Resin/Wax=20/40/40)	69	BDTM/Q-10
Acid Value (KOH mg/g)	0.1	ASTM D 974
Melt Viscosity BRF, @160°C, cps	1,300	ASTM D 3236
<b>@180</b> ℃, cps	380	ASTM D 3236
@200°ℂ, cps	150	ASTM D 3236
Molecular Weight (G.P.C, Mn)	1,400	
(G.P.C, Mw)	2,800	
(G.P.C, Mz)	5,500	
D	2.0	

### **PACKING**

**BONROY**° **O-1098** is available both in 25Kg multi-ply paper bags and 500kg bags.

# STORAGE

**BONROY**° **O-1098** should be stored in cool ventilated dry place. Recommended temperature no exceeding 40°C.