



BONROY INTERNATIONAL LIMITED.

ZIBO NEW MATERIAL TRADING CENTER, PLAZA
A, NORTHEASTREN CORNER OF BEIJING ROAD
AND RENMIN ROAD, ZHANGDIAN, ZIBO,
SHANDONG, P.R. CHINA.

TEL: 0086-533-8170985

www.bonroy-int.com

Technical Data Sheet: G-110

PRODUCT DESCRIPTION

G-110 is C5 piperylene modified C5/C9 hydrocarbon resin which has light color, low odor and narrow molecular weight distribution.

G-110 has outstanding compatibility with EVA and SBS. It's widely used in EVA based HMA such as woodworking Glue, bookbinding.

It's also can used in SIS/SBS/ NR based adhesive such as label, tape, shoe adhesive etc.

TYPICAL PROPERTIES

Appearance		Yellowish Granule
Color Gardner	in 50% toluene	4.0 max
Softening Point	°C	106-115
Ash Content	(wt.%)	0.05 max
Acid Value	(KOH mg/g)	0.30 max
Melt Viscosity	CPS(200 °C)	100 max
Molecular Weight	Mn	820
	Mw	1320
	Mz	2100
	Mw/Mn	1.6
Flash Point	°C	275 min
Specific Gravity	20/20 °C	0.99-1.04
Wax Cloud Point	(Wax:Resin:EVA=25:45:30)°C	85 max
Solubility	28%EVA	Transparent
	SBS	Transparent

PACKAGING

Packed in craft paper bags laminated with PE bags, 25kgs net weight and we also supply the packing according client request.

The information in this bulletin is believed to be accurate, but all recommendations are made without warranty since the conditions of use are beyond BONROY INTERNATIONAL LIMITED's control. The listed properties are illustrative only, and not product specifications. BONROY INTERNATIONAL LIMITED disclaims any liability in connection with the use of the information, and does not warrant against infringement by reason of the use of its products in combination with other material or in any process.