



益冠
BONROY

BONROY INTERNATIONAL LIMITED.

ZIBO NEW MATERIAL TRADING CENTER, PLAZA A,
NORTHEASTERN CORNER OF BEIJING ROAD AND
RENMIN ROAD, ZHANGDIAN, ZIBO, SHANDONG, P.R.
CHINA.

TEL: 0086-533-8170985

www.bonroy-int.com

TECHNICAL DATA SHEET

BTAC-1106

BTAC-1106 is 100% C5 Aliphatic hydrocarbon resin. It's general type C5 resin for hot melt adhesive which has good balance between initial adhesive and holding power.

The major usages of BTAC-1106 are tackify a variety of adhesive polymers including natural rubber, synthetic polyisoprene, APAO, SIS and EVA.O-1098 also can be used in road marking paint and tire rubber.

SPECIFICATIONS

| | | |
|--|----------|-------------|
| Softening Point (Ring & Ball, °C) | 98 – 102 | ASTM E 28 |
| Initial Color (Yellow Index) | 30 Max | ASTM D 6166 |
| Wax Cloud Point (EVA/Resin/Wax=20/40/40) | 100 Max | BDTM/Q-10 |

TYPICAL PROPERTIES

PACKING

BTAC-1106 is available both in 25Kg multi-ply paper bags and 500kg bags.

STORAGE

BTAC-1106 should be stored in cool ventilated dry place. Recommended temperature no exceeding 40°C.