



BONROY INTERNATIONAL LIMITED

ZIBO NEW MATERIAL TRADING CENTER, PLAZA A,
NORTHEASTERN CORNER OF BEIJING ROAD AND RENMIN ROAD,
ZHANGDIAN, ZIBO, SHANDONG, P.R. CHINA

TEL: 0086-533-8170985

www.bonroy-int.com

TECHNICAL DATA SHEET

BTAC-C120

BTAC-C120 resins are pale yellow catalytic polymerization aromatic hydrocarbon resins obtained from polymerizing unsaturated aromatic olefins and diolefins derived from the process of thermal cracking of naphtha.

BTAC-C120 used for rubber compounding agent for tires, tubes, rubber coated clothes, and it can be used in CR adhesive and SBR adhesive, also can be worked as binder for asphalt used in road paving.

TYPICAL PROPERTIES

Softening Point (Ring & Ball, °C)	115-125	ASTM E 28
Initial Color (Gardner in 50% toluene)	4 - 7	ASTM D1544
Melt Viscosity BFR, @200°C, cps	180	ASTM D 3236
Bromine Value (Br ₂ g/100g)	25 max	ASTM D 1195
Acid Value (KOH Mg/g)	0.1 max	ASTM D 974
Specific Gravity (20/20 °C)	1.08	
Ash content (wt.%)	0.05 max	
Flash Point (°C)	275 min	
Heat Resistance (200°C 3h, Gardner)		ASTM D1544
Molecular Weight (G.P.C, Mw)	1,800	

PACKING

BTAC-C120 is available both in 25Kg multi-ply paper bags and 500kg bags.

STORAGE

BTAC-C120 should be stored in cool ventilated dry place. Recommended temperature no exceeding 35°C.

The information in this bulletin is believed to be accurate, but all recommendations are made without warranty since the conditions of use are beyond Puyang United Chemical's control. The listed properties are illustrative only, and not product specifications. Puyang United Chemical disclaims any liability in connection with the use of the information, and does not warrant against infringement by reason of the use of its products in combination with other material or in any process.